



## Processing techniques of acrylic resin in removable and maxillofacial prosthesis: A review

Somayeh Allahyari <sup>1</sup>, Somayeh Niakan <sup>2\*</sup>

1. Department of Dental Technology Prosthodontics, School of Dentistry, Tehran University of Medical Sciences, Tehran, Iran.

2. Department of Prosthodontics, School of Dentistry, Tehran University of Medical Sciences, Tehran, Iran.

### ARTICLE INFO

Article Type:  
Review Article

Received: 23 May. 2018

Revised: 28 Jul. 2018

Accepted: 15 Aug. 2018

\*Corresponding author:

Somayeh Niakan

Department Of Prosthodontics, North Kargar St.,  
Tehran Dental School, Tehran University of Medi-  
cal Sciences, Tehran, Iran.

Tel: +98-912-6060988

Fax: +98-21-84902473

Email: drsomayehniakan@Yahoo.com

### ABSTRACT

Compression molding with heat activation for resin polymerization is the conventional method for processing acrylic resin in removable and maxillofacial prosthesis. Overtime, different processing methods have been improved to overcome physical and chemical problems in cured resin with conventional technique. Enough knowledge about each method is necessary for both dentist and laboratory technician. The aim of this study is review the improved techniques for curing resin and comparison between them. An online search of PubMed, Scopus, Science Direct, and Google Scholar was conducted using key words “denture possessing technique” and “acrylic resins” from 1970 until September 2018. The most common and successful techniques are injection molding and conventional methods. CAD/CAM technology is especially useful for maxillofacial prosthesis but still needs more studies.

**Keywords:** Denture possessing technique, Acrylic resins, Maxillofacial prosthesis, Removable prosthesis.

### Introduction

Removable and maxillofacial prosthesis is used for patients to restore esthetic and function. Most of them are fabricated from poly methyl methacrylate resin (PMMA) with or without metal framework. Adequate materials and processing methods should have some requirements such as adequate resistance, hardness and strength, dimensional and color stability, easy cleansing and fabrication, non toxic and inexpensive [1].

Compression molding with heat activation for resin polymerization is the conventional method for processing acrylic resin. In this method after wax elimination,

the dough is packed in the gypsum mold, and the flasks are placed under pressure in a water bath to initiate polymerization of the resin. This technique is more familiar for dental technician; however, there are some problems during and after resin polymerization such as polymerization and thermal shrinkage, dimensional changes of denture bases and changes in occlusal vertical dimension. Dimensional changes are related to the different coefficients of thermal expansion of the acrylic resin and the gypsum matrix that result in an internal elastic stress in the cured base [2,3]. Therefore, different processing methods have been improved to reduce physical and chemical problems

in cured acrylic resin in denture bases and maxillofacial prosthesis. They should be fabricated with least dimensional changes, on the other hand maxillary obturators should be hollow to have less weight so choosing the suitable method for obtaining successful treatment outcome is important for both dentist and laboratory technician.

The aim of this study is review the literature for improved methods for processing acrylic resin and comparison between them. Among methods, five processing methods are most popular and more discussed in literature, including: Pour resin technique (Fluid.T), injection molding technique, light activated resin, microwave cured technique, CAD/CAM technique. However, up to our research no study has reviewed these five methods in a comparative way, so we focused on the articles that compared between at least two methods.

We reviewed the available papers discussing acrylic resin processing technique. An online search of PubMed, Scopus, Science Direct, and Google Scholar was conducted using key words “denture possessing technique” and “acrylic resins” and “maxillofacial prosthesis” and “removable prosthesis” from 1970 until September 2018. Studies with results not including the comparison or not peer reviewed were excluded.

#### **Pour resin technique (Fluid.T)**

The fluid resin technique, using chemically cured pourable acrylic resins with hydrocolloid molds, was developed in 1955. It has undergone various changes over time [4]. Nowadays, a new processing technique for fluid resin is introduced. Curing temperature is 45 C with a pressure chamber. It was claimed that warp age of the denture base is virtually eliminated and optimal translucency is provided. The most difference between these resins and the conventional chemically activated resins is the smaller size of the powder that results in a more fluid mix in first [1]. In this technique fluid mix poured into a reversible hydrocolloid mold. The good adaptation of denture base in this technique comes from atmospheric pressure around the mold because hydro-flask cut down the air trapping in the processed resin.

Other advantages are simplification of flasking, deflasking and finishing procedure. Decreased probability of damage to prosthetic teeth and denture bases during flasking. On the other hand disadvantages are noticeable shifting of prosthetic teeth during process-

ing. Poor bonding between the denture base material & acrylic resin teeth and technique sensitivity [4,5].

#### **Injection-molding technique**

The injection-molding technique is introduced in 1942. In this technique denture base fabricated in special flask. At first one half of flask is filled with dental stone & master cast is inserted in it, then sprues are attached to the wax denture base, flask is filled with freshly dental stone. After wax elimination the resin is injected in the mold cavity, then flask is placed in boiling water bath for polymerization of denture base resin. As it polymerizes, additional resin is injected into the mold cavity and reduced polymerization shrinkage [6]. The most advantage of this method is the constant injection pressure compensates for the gradual shrinkage of the acrylic resin as the denture base is cured under heat and pressure. It was resulting in denture bases that fit with a smaller degree of error [7]. Other advantages are: no need to open and press, the flask is resisted to corrosion, better accuracy and adaptation to underlying soft tissue, less changes in vertical dimension and reduced need for occlusal adjustment after processing, more strength and density in denture base [8]. Disadvantages are; high cost and technique sensitivity, some researcher reported nosignificant advantages over conventional method [6].

#### **Light cured technique**

This method composed of composite matrix of urethane dimethacrylate, micro fine silica & high molecular weight acrylic resin monomer that was activated with visible light camphorquinone as an initiator. At first put resin on the master cast in a light chamber with the visible light of 400 to 500nm for about 10 minutes. After initial curing of the resin base, the teeth are repositioned on the base using a light-cured template, followed by a final cure in the light chamber [1].

#### **Advantages are:**

- No allergy to PMMA (there isn't any methyl methacrylate monomer).
- Less polymerization shrinkage than conventional resins.
- Good adaptation to the underlying tissues.

#### **Disadvantages are**

- Deformation of the dentures during function.

- Inferior bond strength of VLC resins to resin denture.
- Some concerns about biocompatibility of VLC denture base resins [1].

### Microwave activated resin

It was introduced in 1968, use of resin materials with microwave activation. The procedure was improved with a special glass fiber-reinforced plastic flask [9]. The resin is mixed and exposed to radio waves with a short curing cycle of about 3 minutes at 500 to 600 W/cycle. As the degree of polymerization increases, monomer content decreases proportionally. This technique has some advantages; it is cleaner, denture tooth movements is lower, equal distribution of temperature throughout the resin and gypsum mold, and increased homogeneity of the dough. Disadvantages are high equipment expenses and fragility of the plastic flasks [8].

### CAD/CAM technique

Use of CAD/CAM for processing denture can be done in two types: additive (RP) or subtractive (milling). Subtractive technique is done by milling from a block by a CNC machine. The CAM software automatically transfers the CAD model into tool path for the CNC machine [10]. In RP physical models is build up from three-dimensional electronic information by layered manufacturing. Advantages are reduced treatment sessions, use of pre-polymerized acrylic resin, decreased shrinkage, increase strength and fit of dentures, also ability to form complex anatomic features especially in maxillofacial prosthesis. Disadvantages are some challenges due to impression-taking and OVD recording procedures and maintenance of lip support and mandibular occlusal plane, which are same as conventional process, expensive materials and increased laboratory cost [11,12].

## Discussion

Different methods of processing denture base were devised to overcome the problems of the conventional method, however each of these methods has some disadvantages that make it difficult for dentist or technician to choose. Antonopoulos et al. compared the fluid resin dentures with the dentures constructed by the compression-molding heat-curing technique and found the fluid resin complete dentures underwent larger dimensional changes than the conventionally processed heat-cured dentures [13]. Al-Aaloosi et al. found that linear dimensional changes in fluid resin

is less than heat-cured resins but decrease in vertical dimension of occlusion still exists as a disadvantage of the fluid resin systems [5]. Articles related to this method were limited to the 1980s, and practically this method did not attract much support. Gharachahi et al. found significant difference in flexural strength of injection-molded acrylic resin that was higher than conventional method [8]. They also resulted in a higher dimensional accuracy in injection molded technique compared to conventional molding [6]. Sykora et al. reported higher dimensional accuracy for injection-molding technique, in comparison to the conventional method and determined that was related to smaller resin particles compared to the conventional acrylic resin and lower polymerization temperature [14]. Nagaviro et al. demonstrated that dimensional change of the injection molding material after processing was less than compression molding material. They also suggested that long curing procedure provided less dimensional change [16]. Parvizi et al found that linear dimensional changes of conventionally resin is superior than injection molded denture base materials [7]. Chintalacheruvu found injection molding techniques exhibited less processing errors as compared to compression molding technique with statistical significance [17]. However Keenan et al found little advantage of injection molding toward conventional compression molding [15].

Today, injection molding technique is very popular, and companies offer a variety of advanced devices and equipment for this method. Some of examples are: Swiss Jet (Heat & Self cure), Success (Heat cure), Ivocap (high impact/ Heat cure), Ivobase (Ivobase hybrid or Ivobase high impact/Self cure), Deflex (Polyamid or Self cure). Ali et al showed that light and heat-cured PMMA has significantly higher surface hardness, flexural strength, and flexural modulus than heat-only cured and self-cured denture base systems [18].

Hashem et al demonstrated that light cured has better mechanical properties including flexural, tensile and compressive strength than conventional heat cured acrylic resin [19]. This technique also failed to find a higher position than conventional technique and is limited to repair condition because of some problems such as deformation of the dentures during function and inferior bond strength of VLC resins to resin denture [1,20]. Nelson et al investigated the vertical dimension of occlusion in complete dentures after processing with conventional and microwave procedures. It was less than 1 mm in both methods and is clinically

acceptable [21]. Jadhav et al found microwave PMMA has higher impact strength than conventional PMMA [22]. However Al-Dobaie et al concluded microwave curing technique increased the flexural strength of the acrylic resin but reduced its impact strength [23]. Compagnoni reported same porosity between microwave and conventional heat-polymerized denture base resin. Although studies on this technique continue, but because of the expensive equipment, microwave technique could not be used as a routine in laboratories [24].

Goodacre et al compared the conventional technique with pour, injection, and CAD-CAM techniques and found the most accuracy for CAD-CAM fabrication technique [25]. They also demonstrated that tooth movement is detectable for all processing technique. However, CAD-CAM monolithic technique has the high reproducibility, followed by pack-and-press, CAD-CAM-bonded, injection, and fluid resin [26]. Computer-aided technology for complete dentures is in advanced. However, more prospective clinical trials are necessary to validate this technology [11].

Uzun et al ranked the transverse strength of 4 acrylic resins as high to low respectively: Microwave-cured acrylic resin  $\geq$  Heat-cured resins  $\geq$  self cured resin  $\geq$  visible light-cured acrylic resin showed the lowest [27]. Jorge et al indicated that autopolymerized resins are more cytotoxic than the heat-polymerized denture base resins and microwave cured resin has least cytotoxicity, probably because of less content of monomers. Increasing the polymerization time in light cured resin may decrease resin toxicity [28].

Some studies demonstrated that heat activated resins produced higher bond strength to denture teeth than the microwave activated, visible light cure, pour-type or self cure acrylic resins [29-33]. Nevertheless another studies indicated higher bond strengths with microwave activated resin than with the heat-activated resins and recommended use of bonding agent with a visible light-cure resin [34-36].

## Conclusion

Few studies have compared all types and techniques of resin processing in terms of cytotoxicity, color stability, bond and fracture strength at the present time. The most common and successful techniques are Injection molding and conventional methods. CAD/CAM technology is especially useful for maxillofacial prosthesis but it still needs more studies.

## Conflict of Interest

There is no conflict of interest to declare.

## References

- [1] Zarb GA, Hobkirk J, Eckert S, Jacob R. Prosthodontic Treatment for Edentulous Patients-E-Book: Complete Dentures and Implant-Supported Prostheses. Elsevier Health Sciences; 2013 Nov 21.
- [2] Dukes BS, Fields H, Morris JC, Jewell A. A comparative study of changes in vertical dimension of occlusion using different investing mediums. *Journal of Prosthetic Dentistry*. 1983 Apr 1; 49(4):568-71.
- [3] Gharechahi J, Asadzadeh N, Shahabian F, Gharechahi M. Flexural strength of acrylic resin denture bases processed by two different methods. *Journal of dental research, dental clinics, dental prospects*. 2014; 8(3):148.
- [4] Antomopoulos AN. Dimensional and occlusal changes in fluid resin dentures. *The Journal of prosthetic dentistry*. 1978 Jun 1; 39(6):605-15.
- [5] Al-Aaloosi SR, Fatah NA. Tooth movement in maxillary complete dentures fabricated with fluid resin polymer using different investment materials. *Journal of Baghdad college of dentistry*. 2012; 24(3):18-24. Gharechahi J, Asadzadeh N, Shahabian F, Gharechahi M. Dimensional changes of acrylic resin denture bases: Conventional versus injection-molding technique. *Journal of dentistry (Tehran, Iran)*. 2014 Jul; 11(4):398.
- [6] Parvizi A, Lindquist T, Schneider R, Williamson D, Boyer D, Dawson DV. Comparison of the dimensional accuracy of injection-molded denture base materials to that of conventional pressure-pack acrylic resin. *J Prosthodont*. 2004 Jun; 13(2):83-9.
- [7] Gharechahi J, Asadzadeh N, Shahabian F, Gharechahi M. Flexural strength of acrylic resin denture bases processed by two different methods. *Journal of dental research, dental clinics, dental prospects*. 2014; 8(3):148-152.
- [8] Takamata T, Setcos JC, Phillips RW, Boone ME. Adaptation of acrylic resin dentures as influenced by the activation mode of polymerization. *The Journal of the American Dental Association*. 1989 Aug 1; 119(2):271-6.
- [9] Bilgin MS, Baytaroglu EN, Erdem A, Dilber E. A

- review of computer-aided design/computer-aided manufacture techniques for removable denture fabrication. *European journal of dentistry*. 2016 Apr; 10(2):286-91.
- [10] Bidra AS, Taylor TD, Agar JR. Computer-aided technology for fabricating complete dentures: Systematic review of historical background, current status, and future perspectives. *J Prosthet Dent* 2013;109:361-6.
- [11] Tasopoulos T, Kouveliotis G, Polyzois G, Karathanasi V. Fabrication of a 3D printing definitive obturator prosthesis: A Clinical report. *Actastomatologica Croatica*. 2017 Mar 17; 51(1):53-9.
- [12] Antomopoulos AN. Dimensional and occlusal changes in fluid resin dentures. *The Journal of prosthetic dentistry*. 1978 Jun 1; 39(6):605-15.
- [13] Sykora O, Sutow EJ. Comparison of the dimensional stability of two waxes and two acrylic resin processing techniques in the production of complete dentures. *Journal of oral rehabilitation*. 1990 May; 17(3):219-27.
- [14] Keenan PL, Radford DR, Clark RK. Dimensional change in complete dentures fabricated by injection molding and microwave processing. *The Journal of prosthetic dentistry*. 2003 Jan 1; 89(1):37-44.
- [15] Nagaviroj N, Wanitchanont K, Kanchanasavita W, Wonglamsam A. Dimensional stability of compression and injection molding denture bases in long and short curing procedures. *M Dent J*. 2016 May-August; 36(2):155-163.
- [16] Chintalacheruvu VK, Balraj RU, Putchala LS, Pachalla S. Evaluation of three different processing techniques in the fabrication of complete dentures. *Journal of International Society of Preventive & Community Dentistry*. 2017 Jun; 7(Suppl 1):S18.
- [17] Ali IL, Yunus N, Abu-Hassan MI. Hardness, flexural strength, and flexural modulus comparisons of three differently cured denture base systems. *Journal of Prosthodontics: Implant, Esthetic and Reconstructive Dentistry*. 2008 Oct; 17(7):545-9.
- [18] Hashem M, Alsaleem SO, Assery MK, Abdeslam EB, Vellappally S, Anil S. A comparative study of the mechanical properties of the light-cure and conventional denture base resins. *Oral Health Dent Manag*. 2014 Jun; 13(2):311-5.
- [19] Cunningham JL. Shear bond strength of resin teeth to heat-cured and light-cured denture base resin. *Journal of oral rehabilitation*. 2000 Apr; 27(4):312-6.
- [20] Nelson MW, Kotwal KR, Sevedge SR. Changes in vertical dimension of occlusion in conventional and microwave processing of complete dentures. *Journal of Prosthetic Dentistry*. 1991 Feb 1; 65(2):306-8.
- [21] Jadhav R, Bhide SV, Prabhudesai PS. Assessment of the impact strength of the denture base resin polymerized by various processing techniques. *Indian J Dent Res*. 2013 Jan-Feb; 24(1):19-25. doi: 10.4103/0970-9290.114926.
- [22] Eglal G, Al-Dobaei, Nadia A. Badr, Dalia M. Abdel Hamid. The effect of curing techniques of denture base resins on strength characteristics under different loading modes. *Egyptian Dental Journal*. 2012 October; 58: 3927-3937.
- [23] Compagnoni MA, Barbosa DB, de Souza RF, Pero AC. The effect of polymerization cycles on porosity of microwave-processed denture base resin. *The Journal of prosthetic dentistry*. 2004 Mar 31; 91(3):281-5.
- [24] Goodacre BJ, Goodacre CJ, Baba NZ, Kattadiyil MT. Comparison of denture base adaptation between CAD-CAM and conventional fabrication techniques. *J Prosthet Dent*. 2016 Aug; 116(2):249-56. doi: 10.1016/j.prosdent.2016.02.017. Epub 2016 Apr 23.
- [25] Goodacre BJ, Goodacre CJ, Baba NZ, Kattadiyil MT. Comparison of denture tooth movement between CAD-CAM and conventional fabrication techniques. *J Prosthet Dent*. 2018 Jan; 119(1):108-115. doi: 10.1016/j.prosdent.2017.02.009. Epub 2017 May 12.
- [26] Uzun G, Hersek N. Comparison of the fracture resistance of six denture base acrylic resins. *J Biomater Appl*. 2002 Jul; 17(1):19-29.
- [27] Jorge JH, Giampaolo ET, Machado AL, Vergani CE. Cytotoxicity of denture base acrylic resins: a literature review. *The Journal of prosthetic dentistry*. 2003 Aug 1; 90(2):190-3.
- [28] Hayakawa I, Hirano S, Nagao M et al. Adhesion



of a new light polymerized denture base resin to resin teeth and denture base materials. *Int J Prosthodont* 1991; 4: 561–568.28.

[29] Buyukyilmaz S, Ruyter IE. The effect of polymerization temperature on the acrylic resin denture base-tooth bond. *Int J Prosthodont* 1997; 10: 49–54.33.

[30] Vallittu PK, Ruyter IE. The swelling phenomenon of acrylic resin polymer teeth at the interface with denture base polymers. *J Prosthet Dent* 1997; 78: 194–199.

[31] Cunningham JL. Shear bond strength of resin teeth to heat-cured and light cured denture base resin. *J Oral Rehabil* 2000; 27: 312–316.29.

[32] Patil SB, Naveen BH, Patil NP. Bonding acrylic teeth to acrylic resin denture bases: a review. *Gerodontology*. 2006 Sep; 23(3):131-9.

[33] Yamauchi M, Iwahori M, Sakai M et al. Comparative bond strengths of plastic teeth to microwave curing, heat curing and 4-META containing denture base resins. *Gifu Shika Gakki Zasshi* 1989; 16: 542–550.26.

[34] Geerts GAVM, Jooste CH. A comparison of the bond strengths of microwave and water bath cured denture material. *J Prosthet Dent* 1990; 70: 406–409.27.

[35] Clancy JM, Boyer DB. Comparative bond strengths of light cured, heat-cured and autopolymerising denture resins to denture teeth. *J Prosthet Dent* 1989; 61: 457–462.25.

*Please cite this paper as:*

Allahyari S, Niakan S; Processing techniques of acrylic resin in removable and maxillofacial prosthesis: A review. *J Craniomax Res* 2018; 5(3): 99-104